


April 7, 2009,v1.0

Processing Guides for WONDERLITE® PC-110L

- A Pre-drying 120°C x 4 hrs
 depending on a) Humidity
 b) Storage conditions
 c) Dryer's performance

B. Barrel Setting Profile



Grade / Application		Nozzle	Compression zone	Feeding zone	Mold Temperature *
PC-110L	max.(°C)	310	320	300	70 -120
	min.(°C)	250	250	230	

- * varying with a) Thickness of molded articles
 b) Cooling system design
 c) Gate and runner system

NOTE :

1. Keep the resin from dust and contamination during handling and production.
2. Do not retain the hot melt at the barrel for a long time between injection cycles.
3. Temperature setting of manifold system should not exceed 330°C to avoid melt from degrading.

For further information, please contact your local agent or fax to CHIMEI-ASAHI Technical Services Dept. at 886-6-2667983/2667984